

AD-A193 208


PREPARATION AND DEVELOPMENT OF ADVANCED BATTERY
CATALYSTS(U) EIC LABS INC NORWOOD MA W P KILROY ET AL.
01 OCT 87 C-868 NSWC-TR-87-104 N60921-86-C-0209


1/1

UNCLASSIFIED

F/G 10/3

NL





NSWC TR 87-184

AD-A193 208

PREPARATION AND DEVELOPMENT OF ADVANCED BATTERY CATALYSTS

BY W. P. KILROY (NSWC)
K. M. ABRAHAM AND M. ALAMGIR (EIC)

RESEARCH AND TECHNOLOGY DEPARTMENT

1 OCTOBER 1987

Approved for public release; distribution is unlimited.



NAVAL SURFACE WARFARE CENTER

Dahlgren, Virginia 22448-5000 • Silver Spring, Maryland 20903-5000

DTIC
ELECTE
S APR 13 1988 D
E

88 4 11 258

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE

REPORT DOCUMENTATION PAGE

1a REPORT SECURITY CLASSIFICATION UNCLASSIFIED			1b RESTRICTIVE MARKINGS A193208	
2a SECURITY CLASSIFICATION AUTHORITY			3 DISTRIBUTION AVAILABILITY OF REPORT	
2b DECLASSIFICATION/DOWNGRADING SCHEDULE				
4 PERFORMING ORGANIZATION REPORT NUMBER(S) C-868			5 MONITORING ORGANIZATION REPORT NUMBER(S) NSWC TR 87-104	
6a NAME OF PERFORMING ORGANIZATION EIC Laboratories, Inc.		6b OFFICE SYMBOL (If applicable)		7a NAME OF MONITORING ORGANIZATION Naval Surface Warfare Center White Oak Laboratory
6c ADDRESS (City, State, and ZIP Code) 111 Downey Street Norwood, Massachusetts 02062		7b ADDRESS (City, State, and ZIP Code) 10901 New Hampshire Avenue Silver Spring, Maryland 20903-5000		
8a NAME OF FUNDING/SPONSORING ORGANIZATION Naval Surface Warfare Center		8b OFFICE SYMBOL (If applicable) R33		9 PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N60921-86-C-0209
8c ADDRESS (City, State, and ZIP Code) 10901 New Hampshire Avenue Silver Spring, Maryland 20903-5000		10 SOURCE OF FUNDING NUMBERS		
		PROGRAM ELEMENT NO. 65502	PROJECT NO.	TASK NO. 411415-02 WORK UNIT ACCESSION NO. R76EAF
11 TITLE (Include Security Classification) Preparation and Development of Advanced Battery Catalysts				
12 PERSONAL AUTHOR(S) Kilroy, W. P. (NSWC); Abraham, K. M. and Alamgir, M. (EIC)				
13a TYPE OF REPORT Interim Report	13b TIME COVERED FROM Aug 1986 to Feb 1987	14 DATE OF REPORT (Year, Month, Day) 1987, October, 1		15 PAGE COUNT 54
16 SUPPLEMENTARY NOTATION				
17 COSATI CODES			18 SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB-GROUP		
07	04		Catalysis, Lithium Batteries, Thionyl Chloride	
19 ABSTRACT (Continue on reverse if necessary and identify by block number)				
<p>New catalysts which improve the discharge performance of Li/SOCl_2 cells have been identified. These catalysts were obtained by thermal treatment of acetylene black carbon doped with the precursors, $\text{Co}(\text{NO}_3)_2$, manganese phthalocyanine (MnPc) or vanadium phthalocyanine oxide (VOpc). The latter two materials appear to be superior to many catalysts presently available for use in Li/SOCl_2 cells. Compared with uncatalyzed cells, MnPc-containing cells showed a 60% increase in cell capacity and a 10% increase in cell voltage at room temperature. VOpc-containing cathodes increased the cell capacity by 50% and cell voltage by 10% under the same conditions. The use of VOpc also resulted in significant improvements in cell performance at low temperatures, e.g., at -30°C.</p>				
20 DISTRIBUTION AVAILABILITY OF ABSTRACT <input type="checkbox"/> UNCLASSIFIED UNLIMITED <input checked="" type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21 ABSTRACT SECURITY CLASSIFICATION UNCLASSIFIED	
22a NAME OF RESPONSIBLE INDIVIDUAL William P. Kilroy			22b TELEPHONE (Include Area Code) (202) 394-1513	22c OFFICE SYMBOL Code R33

DD FORM 1473, 84 MAR

83 APR edition may be used until exhausted

All other editions are obsolete

SECURITY CLASSIFICATION OF THIS PAGE

U.S. Government Printing Office: 1986 607 044

UNCLASSIFIED

FOREWORD

This interim report describes some initial studies to evaluate new catalytic materials to improve the performance of high energy density, active lithium batteries.

This work is part of a collaborative effort between NSWC and EIC Laboratories to understand the fundamental mechanism of electrocatalysis in Li/SOCl_2 cells to improve their overall safety and to increase their performance to meet operational requirements of new Navy mine batteries.

Funding for this effort was provided by the Office of Naval Technology High Energy Battery Technology Project (Mines Block), and the NSWC Navy Small Business Innovative Research Program.

Approved by:

William T. Messick
WILLIAM T. MESSICK, Acting Head
Materials Division

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Distribution/	
Availability	

A-1



CONTENTS

<u>Chapter</u>		<u>Page</u>
1	INTRODUCTION.	1
2	EXPERIMENTAL.	3
3	RESULTS AND DISCUSSION.	5
	DISCHARGE BEHAVIOR OF Li/SOCl ₂ CELLS USING CATHODES DOPED WITH COBALT CARBONYLS.	26
	DISCHARGE BEHAVIOR OF Li/SOCl ₂ CELLS CONTAINING TRANSITION METAL COMPLEX-CATALYZED CATHODES.	26
	MECHANISM OF ELECTROCATALYSIS IN Li/SOCl ₂ CELLS.	33
4	CONCLUSIONS	41
	REFERENCES.	43
	DISTRIBUTION.	(1)

ILLUSTRATIONS

<u>Figure</u>		<u>Page</u>
1	DISCHARGE PLOTS OF LABORATORY Li/SOCl_2 CELLS CONTAINING $\text{Co(NO}_3)_2$ -DOPED CATHODES, HEAT- TREATED AT 400°C , AND BASELINE CATHODE.	7
2	DISCHARGE PLOTS OF LABORATORY Li/SOCl_2 CELLS CONTAINING $\text{Co(NO}_3)_2$ -DOPED CATHODES, HEAT- TREATED AT 900°C , AND BASELINE CATHODE.	8
3	DISCHARGE PLOTS OF LABORATORY Li/SOCl_2 CELLS CONTAINING $\text{Co(NO}_3)_2$ -DOPED CATHODES, HEAT- TREATED AT 400°C , AND BASELINE CATHODE.	9
4	DISCHARGE PLOTS OF LABORATORY Li/SOCl_2 CELLS CONTAINING CATHODES DIPPED IN 7% $\text{Co(NO}_3)_2$ SOLUTION AND DRIED AT 130°C , AND BASELINE CATHODE	10
5	DISCHARGE PLOTS OF LABORATORY Li/SOCl_2 CELLS CONTAINING CoCO_3 -DOPED CATHODES, HEAT- TREATED AT 900°C , AND BASELINE CATHODE.	11
6	DISCHARGE PLOTS OF LABORATORY Li/SOCl_2 CELLS CONTAINING CoCO_3 -DOPED CATHODES, HEAT- TREATED AT 500°C , AND BASELINE CATHODE.	12
7	DISCHARGE PLOTS OF LABORATORY Li/SOCl_2 CELLS CONTAINING 5 w/o $\text{Co}_2(\text{CO})_8$ AS A CATHODE DOPANT WITH DIFFERENT HEAT TREATMENTS	13
8	DISCHARGE PLOTS OF LABORATORY Li/SOCl_2 CELLS CONTAINING $\text{Co}_2(\text{CO})_8$, SINTERED AT 300°C , AS CATHODE DOPANT	14
9	DISCHARGE PLOT OF A LABORATORY Li/SOCl_2 CELL CONTAINING 5 w/o $\text{Co}_2(\text{CO})_8$, SINTERED AT 200°C , AS CATHODE DOPANT.	15
10	DISCHARGE PLOTS OF LABORATORY Li/SOCl_2 CELLS CONTAINING $\text{Co}_4(\text{CO})_{12}$, SINTERED AT 200°C , AS CATHODE DOPANT.	16
11	DISCHARGE PLOTS OF LABORATORY Li/SOCl_2 CELLS CONTAINING 5 w/o $\text{Co}_4(\text{CO})_{12}$, SINTERED AT 600°C , AS CATHODE DOPANT AT DIFFERENT CUR- RENT DENSITIES.	17
12	DISCHARGE PLOT OF LABORATORY Li/SOCl_2 CELLS CONTAINING 5% VOPc -DOPED, AND BASELINE CATHODES.	18
13	DISCHARGE PLOTS OF LABORATORY Li/SOCl_2 CELLS CONTAINING 5% MnPc -DOPED, AND BASELINE CATHODES.	19

ILLUSTRATIONS (Cont.)

<u>Figure</u>		<u>Page</u>
14	DISCHARGE PLOTS OF LABORATORY Li/SOCl ₂ CELLS CONTAINING 5% CoPc-DOPED, AND BASELINE CATHODES.	20
15	DISCHARGE PLOT OF A CELL CONTAINING 5% VOPc- DOPED CATHODE	28
16	DISCHARGE PLOT OF A CELL CONTAINING 5% MnPc- DOPED CATHODE	29
17	DISCHARGE PLOT OF A CELL CONTAINING 5% CoPc- DOPED CATHODE	30
18	DISCHARGE PLOT OF AN UNCATALYZED CELL	31
19	AMBIENT TEMPERATURE DISCHARGE PERFORMANCE OF LABORATORY Li/SOCl ₂ CELLS CONTAINING 5 w/o OF THE Co-TAA-DOPED CATHODES PREPARED BY THE TEM- PLATE SYNTHESIS	32
20	IR SPECTRUM OF Co-TAA SYNTHESIZED BY THE CONVEN- TIONAL METHOD	38
21	IR SPECTRUM OF Co-TAA PREPARED BY THE TEMPLATE SYNTHESIS	39


TABLES

<u>Table</u>		<u>Page</u>
1	DISCHARGE RESULTS FOR Li/SOCl ₂ CELLS CONTAINING Co(NO ₃) ₂ -DOPED CATHODES [DISCHARGE CURRENT IS 210 mA (10 mA/cm ²)]	6
2	DISCHARGE RESULTS FOR Li/SOCl ₂ CELLS CONTAINING CoCO ₃ -DOPED CATHODES [CURRENT = 210 mA (10 mA/ cm ²)]	21
3	DISCHARGE RESULTS FOR Li/SOCl ₂ CELLS CONTAINING Co ₂ (CO) ₈ -DOPED CATHODES [CURRENT = 210 mA (10 mA/cm ²) EXCEPT WHERE NOTED]	22
4	DISCHARGE RESULTS FOR Li/SOCl ₂ CELLS CONTAINING Co ₄ (CO) ₁₂ -DOPED CATHODES [CURRENT = 210 mA (10 mA/ cm ²) EXCEPT WHERE NOTED]	23
5	DISCHARGE RESULTS FOR Li/SOCl ₂ CELLS CONTAINING TRANSITION METAL COMPLEX-DOPED CATHODES DISCHARGED AT ROOM TEMPERATURE	24
6	DISCHARGE RESULTS OF Li/SOCl ₂ CELLS CONTAINING (5%) TRANSITION METAL COMPLEX-DOPED CATHODES AT -30°C AT 10 mA/cm ²	25
7	X-RAY DATA FOR THE UNDISCHARGED CATHODES CON- TAINING THE VARIOUS DOPANTS.	34
8	X-RAY DATA FOR THE CATHODE OF A Li/SOCl ₂ LABORA- TORY CELL CONTAINING 5 w/o VOPc AS CATHODE DOPANT AND DISCHARGED AT 10 mA/cm ²	35
9	X-RAY DATA FOR THE CATHODE OF A Li/SOCl ₂ LABORA- TORY CELL CONTAINING 5 w/o MnPc AS CATHODE DOPANT AND DISCHARGED AT 10 mA/cm ²	36


CHAPTER 1

INTRODUCTION

The search for catalysts to improve the discharge performance and safety of the Li/SOCl_2 cell is being actively pursued at NSWC. Data available to date¹⁻⁷ indicate that the power capabilities of the Li/SOCl_2 cell can be improved to varying degrees in the presence of cathode catalysts. A variety of materials, when incorporated in the carbon cathode or added to the electrolyte, have been found to increase cell discharge potentials and provide higher capacities at high rates. Some of these materials include finely divided Pt,⁵ Cu powder,⁶ metal phthalocyanine and related macrocyclic complexes,^{1,2,4} and tetracyanoethylene and acetylacetonate complexes of Co and Fe.⁷ Two of the most promising catalysts have been the Fe-phthalocyanine (FePc) complex, I,⁴ and the Cobalt-dibenzotetraazaannulene (Co-TAA) complex, II.^{1,2}



I, Fe-phthalocyanine



II, Cobalt-dibenzotetraazaannulene

Despite empirical observations of improved discharge behavior and better safety characteristics of Li/SOCl_2 cells containing cathodes doped with catalysts, our present understanding of the mechanism of electrocatalysis in this cell is inadequate. This lack of knowledge of the mechanism is evident in the following explanations given by different researchers concerning the discharge mechanism of catalyzed Li/SOCl_2 cells.

- Doddapaneni⁴ initially suggested that FePc changes the mechanism of the SOCl_2 discharge reaction and that the increased capacity was due to the reduction of SO_2 to $\text{Li}_2\text{S}_2\text{O}_4$. However, no analytical work was carried out to verify this. Additional quantitative work is required to support this claim.

- Walsh and Yaniv² suggested that the discharge mechanism in Co-TAA catalyzed cells is different from that in the uncatalyzed cells. They maintained that the final discharge products are LiCl , solvated Li_2O , and S, and since no SO_2 is formed according to this mechanism, the cells are safer. However, little analytical data were presented to substantiate this claim. Our studies on the discharge products from Co-TAA

catalyzed Li/SOCl₂ cells showed no evidence of Li₂O upon analysis by X-ray diffraction and FTIR spectroscopy.¹ The X-ray diffraction pattern of discharged cathodes showed LiCl and S. FTIR analysis of the gaseous products from discharged cells showed that SO₂ is a discharge product in Co-TAA catalyzed cells. Additional analyses are needed to quantitatively determine the discharge products and resolve these different findings.

Clearly, the present understanding of the mechanism of electrocatalysis in Li/SOCl₂ and related cells is poor. Because of the lack of understanding of the mechanism of catalyst-assisted discharge reactions, systematic design of catalysts for the Li/SOCl₂ cell cannot be accomplished without additional studies.




The electrocatalytic activity of CoO, Co₃O₄, or Co towards the reduction of SOCl₂ was investigated to see if the actual catalyst species in the Co-TAA or CoPc impregnated cathodes might be one or more of these oxides, or finely divided Co. In the preparation of Co-TAA- or CoPc-catalyzed carbon cathodes, carbon black containing the complexes is heat treated at 500 to 600°C.^{2,4} At these temperatures, the metal macrocyclic complexes undergo decomposition giving off volatile organic fragments.⁹⁻¹¹ The residues left behind have been claimed to have varying compositions. It is believed that Co-TAA decomposes in a step-wise fashion when heated. At ~400°C, Co-TAA gives off hydrogen to form what appears to be a polymeric material. At higher temperatures, e.g., ~550°C, a substantial loss of carbon and hydrogen along with some nitrogen occurs. At about 800°C there is evidence of complete decomposition of Co-TAA to give metallic cobalt as the residual product. Cobalt oxide (CoO) is also believed to be a component of the residue obtained from the decomposition of Co-TAA. The latter apparently is formed by the reaction of the initially-formed, finely-divided Co with oxygen.

Knowledge of the actual composition of the catalyst is important. Oxides are less expensive and easier to prepare than macrocyclic complexes. Certain limitations of the present transition metal complex catalysts, such as their instability in SOCl₂/LiAlCl₄ or poor high temperature storability of cells, may be overcome with improvements brought about by the knowledge of the actual composition of the catalyst species. It is believed that some of these limitations arise from reactions associated with the organic moiety in the complex. Therefore, eliminating the organic moiety from the catalyst center may result in overall improvements in cell performance.

CHAPTER 2

EXPERIMENTAL

Our scheme for preparing catalyzed carbon cathodes involved treatment of acetylene black carbon with appropriate precursors followed by heat treatment at various temperatures. The chemical reactions that were used to deposit cobalt oxides and finely divided Co in the carbon are depicted in equations (1-4).



Three transition metal phthalocyanine complexes have also been evaluated. These are cobalt phthalocyanine (CoPc), manganese phthalocyanine (MnPc), and vanadium phthalocyanine oxide (VOPc). All these metal complexes are commercially available and their synthesis is rather straightforward. In addition, we have attempted to prepare Co-TAA by simpler synthetic routes and evaluate its catalytic performance.¹²

The precursors used for preparing cobalt oxide-catalyzed cathodes were $\text{Co(NO}_3)_2$ and CoCO_3 . Acetylene black carbon was first doped with the precursors and then sintered at various temperatures prior to fabricating the electrodes. $\text{Co(NO}_3)_2$ was incorporated into the carbon in an aqueous medium. Solutions in water containing required amounts (5, 10, and 20 w/o) of $\text{Co(NO}_3)_2$ were mixed well with carbon, dried at 100°C and the mixture was heat treated at 400 or 900°C under flowing argon.

In order to incorporate CoCO_3 , a slurry of CoCO_3 in ethanol/ H_2O was mixed with carbon, dried at 100°C and then sintered, in argon, at 500 or 900°C .¹³

Teflon-bonded carbon electrodes were made with doped cathodes. The Li/ SOCl_2 laboratory cells used for these studies consisted of a cathode sandwiched between two Li anodes (15 mil thick) pressed onto Ni screens. The cells were filled with 4.0 ml, 1.8M $\text{LiAlCl}_4/\text{SOCl}_2$ electrolyte solution and were truly carbon-limited. A Li strip was also incorporated into the cell as a reference electrode. Typically, the cathodes were 3.5 cm x 3.0 cm x 0.10 cm, and the geometric surface area was 21 cm^2 . The cells were discharged galvanostatically.

CHAPTER 3

RESULTS AND DISCUSSION

Discharge results obtained with $\text{Co}(\text{NO}_3)_2$ catalyzed cells are summarized in Table 1. The capacity in an uncatalyzed cell, hereafter referred to as baseline cell, at 10 mA/cm^2 at room temperature corresponded to a carbon utilization of 1.36 Ah/g . Figures 1 through 14 illustrate discharge behavior of the doped cells compared to a baseline cell whereas Tables 1 through 6 show the capacity normalized (Ah/g carbon) to account for the varying masses of carbon used in each cell. Cathodes containing 5% $\text{Co}(\text{NO}_3)_2$, sintered at 400°C , and those first dipped in a $\text{Co}(\text{NO}_3)_2$ solution followed by a heat treatment at 130°C show evidence of catalytic activity. In Cell No. 1, containing 5 percent $\text{Co}(\text{NO}_3)_2$ -doped cathode, the carbon utilization was 1.59 Ah/g or a 17 percent improvement over the uncatalyzed cell. It appears that the catalytic activity is extremely sensitive to the thermal treatment of the carbon. Figures 1 and 2 compare the behavior of the $\text{Co}(\text{NO}_3)_2$ doped cells with the baseline cathodes. The $\text{Co}(\text{NO}_3)_2$ -doped cathodes, whether sintered at 400 or 900°C , showed no catalytic activity at -30°C as illustrated in Figure 3. A close examination of the data for Cells 3 and 4 in Table 1 shows that the apparent lack of catalytic activity in cathodes doped with 10 percent and 20 percent $\text{Co}(\text{NO}_3)_2$ may be due to a decrease in the total available SOCl_2 at the electrode active sites, because the excess catalyst begins to occupy significant fractions of pore volume. The mass-transport in the cathode is impeded as channels are blocked. The observed capacities of Cells 3 and 4 agree with this explanation because the capacity of Cell 3 is ~85 percent and that of Cell 4 is ~77 percent of the capacity of Cell 1. The decrease in capacity in each cell corresponds approximately to the amount of catalyst added beyond 5 percent.

The behavior of the carbon electrodes that were dipped in $\text{Co}(\text{NO}_3)_2$ solution followed by drying at 130°C is illustrated in Figure 4. These electrodes exhibit higher voltages than the electrodes sintered at 400°C , and their capacities are similar to those sintered at 900°C .

A comparison of the behavior of $\text{Co}(\text{NO}_3)_2$ -containing electrodes heat treated at 400 and 130°C , presented in Figures 1 and 4, suggest that in the latter case the active species probably is $\text{Co}(\text{NO}_3)_2$ itself while in the former case it is an oxide, probably Co_3O_4 . Although the capacity of the cathode is increased as a result of Co_3O_4 doping, the cell discharge potential remains the same as that in the baseline case. When $\text{Co}(\text{NO}_3)_2$ itself is the active catalyst species, the cell discharge voltage is slightly enhanced while the capacity of the cathode shows a decline.

Further studies of these electrodes, especially with respect to optimization of the amount of $\text{Co}(\text{NO}_3)_2$ and the sintering temperature, are warranted because of the promising results from $\text{Co}(\text{NO}_3)_2$ doping. This will be carried out in future studies.

TABLE 1. DISCHARGE RESULTS FOR Li/SOCl_2 CELLS CONTAINING $\text{Co}(\text{NO}_3)_2$ -DOPED CATHODES
[DISCHARGE CURRENT IS 210 mA (10 mA/cm^2)]

Cell No.	Weight Percent of $\text{Co}(\text{NO}_3)_2$	Carbon Sintering Temperature, °C	Discharge Temperature, °C	Mid-Discharge Voltage, V	Capacity**	
					mAh	Ah/g
1	5	400	20	3.04	686	1.59
2	5	400	-30	2.35	406	0.97
3	10	400	20	2.99	406	1.35
4	20	400	20	2.98	470	1.23
5	20	400	-30	2.18	343	0.93
6	5	900	20	3.08	500	1.16
7	5	900	20	3.10	562	1.22
8	5	900	20	3.10	504	1.16
9	10	900	20	3.09	420	0.95
10	*	130*	20	3.13	349	0.90
11	*	130*	-30	2.35	309	0.77

*Finished cathodes dipped in 7% solution followed by drying at 130°C.

**Capacity in cells without catalyst = 1.36 Ah/g.




FIGURE 1. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING Co(NO₃)₂-DOPED CATHODES, HEAT-TREATED AT 400°C, AND BASELINE CATHODE




FIGURE 2. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING Co(NO₃)₂-DOPED CATHODES, HEAT-TREATED AT 900°C, AND BASELINE CATHODE




FIGURE 3. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING Co(NO₃)₂-DOPED CATHODES, HEAT-TREATED AT 400°C, AND BASELINE CATHODE




FIGURE 4. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING CATHODES DIPPED IN 7% Co(NO₃)₂ SOLUTION AND DRIED AT 130°C, AND BASELINE CATHODE




FIGURE 5. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING CoCO₃-DOPED CATHODES, HEAT-TREATED AT 900°C, AND BASELINE CATHODE




FIGURE 6. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING CoCO₃-DOPED CATHODES, HEAT-TREATED AT 500°C, AND BASELINE CATHODE




FIGURE 7. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING 5 w/o Co₂(CO)₈ AS A CATHODE DOPANT WITH DIFFERENT HEAT TREATMENTS




FIGURE 8. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING Co₂(CO)₈, SINTERED AT 300°C, AS CATHODE DOPANT




FIGURE 9. DISCHARGE PLOT OF A LABORATORY Li/SOCl₂ CELL CONTAINING 5 w/o Co₂(CO)₈, SINTERED AT 200°C, AS CATHODE DOPANT




FIGURE 10. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING Co₄(CO)₁₂, SINTERED AT 200°C, AS CATHODE DOPANT




FIGURE 11. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING 5 w/o Co₄(CO)₁₂, SINTERED AT 600°C, AS CATHODE DOPANT AT DIFFERENT CURRENT DENSITIES




FIGURE 12. DISCHARGE PLOT OF LABORATORY Li/SOCl₂ CELLS CONTAINING 5% VOPc-DOPED, AND BASELINE CATHODES




FIGURE 13. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING 5% MnPc-DOPED, AND BASELINE CATHODES




FIGURE 14. DISCHARGE PLOTS OF LABORATORY Li/SOCl₂ CELLS CONTAINING 5% CoPc-DOPED, AND BASELINE CATHODES

TABLE 2. DISCHARGE RESULTS FOR Li/SOCl_2 CELLS CONTAINING CoCO_3 -DOPED CATHODES
 [CURRENT = 210 mA (10 mA/cm^2)]

Cell No.	Weight Percent of CoCO_3	Carbon Sintering Temperature, °C	Discharge Temperature, °C	Mid-Discharge Voltage, V	Capacity*	
					mAh	Ah/g
12	5	500	20	2.91	475	1.25
13	10	500	20	3.01	439	0.98
14	5	900	20	3.12	561	1.37
15	10	900	20	3.15	526	1.28
16	10	900	-30	2.6	274	0.62
17	20	900	20	3.11	340	0.81

*Capacity in cells without catalyst = 1.36 Ah/g at 20°C.

TABLE 3. DISCHARGE RESULTS FOR Li/SOCl_2 CELLS CONTAINING $\text{Co}_2(\text{CO})_8$ -DOPED CATHODES
[CURRENT = 210 mA (10 mA/cm²) EXCEPT WHERE NOTED]

Cell No.	Weight Percent of $\text{Co}_2(\text{CO})_8$	Carbon Sintering Temperature, °C	Discharge Temperature, °C	Mid-Discharge Voltage, V	Capacity*	
					mAh	Ah/g
18	5	300	20	3.10	460	1.24
19	10	300	20	3.05	358	0.83
20	10	300	20	3.1	594	1.09
21	5	600	20	3.12	506	1.12
22	5	200	20	3.10	498	1.23
23	5	200	20	3.09	489	1.34
24	5**	200	20	3.24	599	1.39

*Capacity in cells without catalysts = 1.36 Ah/g.

**Discharge current was 105 mA (5 mA/cm²).

TABLE 4. DISCHARGE RESULTS FOR Li/SOCl_2 CELLS CONTAINING $\text{Co}_4(\text{CO})_{12}$ -DOPED CATHODES
 [CURRENT = 210 mA (10 mA/cm²) EXCEPT WHERE NOTED]

Cell No.	Weight Percent of $\text{Co}_4(\text{CO})_{12}$	Carbon Sintering Temperature, °C	Discharge Temperature, °C	Mid-Discharge Voltage, V	Capacity*	
					mAh	Ah/g
25	5	200	20	3.11	410	1.20
26	5	200	20	3.05	413	1.14
27	10	200	20	3.10	415	1.08
28	10	200	20	3.11	408	1.06
29	5	600	20	3.10	410	0.93
30	10	600	20	3.10	473	0.66
31	5**	600	20	3.26	613	1.40

*Capacity in cells without catalysts = 1.36 Ah/g.

**Discharge current was 105 mA (5 mA/cm²).

TABLE 5. DISCHARGE RESULTS FOR Li/SOCl_2 CELLS CONTAINING TRANSITION METAL COMPLEX-DOPED CATHODES DISCHARGED AT ROOM TEMPERATURE

Cell No.	Complex	Weight Percent of Complex	Carbon Sintering Temperature, °C	Discharge Temperature, °C	Mid-Discharge Voltage, V	Capacity*	
						mAh	Ah/g
32	VOPc	5	600	20	3.34	830	1.98
33	VOPc	10	600	20	3.26	969	1.94
34	MnPc	5	600	20	3.29	866	2.21
35	MnPc	10	600	20	3.09	599	1.43
36	CoPc	5	600	20	3.32	718	1.94

*Capacity in cells without catalyst = 1.36 Ah/g.

TABLE 6. DISCHARGE RESULTS OF Li/SOCl_2 CELLS CONTAINING (5%)
TRANSITION METAL COMPLEX-DOPED CATHODES AT -30°C AT 10 mA/cm^2

<u>Cell No.</u>	<u>Complex</u>	<u>Mid-Discharge Voltage, V</u>	<u>Capacity, Ah/g</u>	
			<u>(2.0V)</u>	<u>(0.0V)</u>
37	VOPc	2.74	0.91	0.97
38	CoPc	2.81	0.51	0.57
39	MnPc	2.71	0.58	0.64
<hr/>				
	Baseline cathode without catalyst	2.60	0.70	1.0

The discharge results obtained by using CoCO_3 as the catalyst precursors are summarized in Table 2. Relevant discharge curves are presented in Figures 5 and 6. The discharge capacities are similar to or less than that obtained in the baseline cell. CoCO_3 doping seems to decrease the capacity of the baseline electrode in proportion to the amount of the added dopant. X-ray analysis of CoCO_3 -doped carbon after heat treatment showed the presence of cobalt carbides and Co_3O_4 (discussed later). It appears that cobalt carbides have little or no catalytic activity on the reduction of SOCl_2 .

DISCHARGE BEHAVIOR OF Li/SOCl_2 CELLS USING CATHODES DOPED WITH COBALT CARBONYLS

As mentioned earlier, the reasoning behind the use of cobalt carbonyls as catalyst precursors has been the incorporation of finely divided metallic cobalt in the carbon cathode.¹⁴ It is possible that such electrodes may also contain cobalt carbides or oxides, the former being formed during heat treatment of the carbonyl and the latter during reactions following the heat treatment with atmospheric oxygen.

Discharge data for cells using cobalt carbonyl-doped cathodes, heat treated at various temperatures, are summarized in Tables 3 and 4. $\text{Co}_2(\text{CO})_8$ was deposited on the carbon from a THF solution and $\text{Co}_4(\text{CO})_{12}$ from a diethyl ether medium. After the carbon was mixed with the respective solutions, the solvent was removed by pumping under a vacuum. The carbon deposited with the cobalt carbonyl was heat treated in Ar at the various temperatures indicated in Tables 3 and 4. Typical discharge curves obtained with these carbon electrodes are given in Figures 7 through 11. Carbon utilization data are presented in Tables 3 and 4. Neither the $\text{Co}_2(\text{CO})_8$ -doped nor the $\text{Co}_4(\text{CO})_{12}$ -doped electrodes showed any evidence for catalytic activity.

DISCHARGE BEHAVIOR OF Li/SOCl_2 CELLS CONTAINING TRANSITION METAL COMPLEX-CATALYZED CATHODES

Transition metal complexes that have so far shown the highest activity in Li/SOCl_2 cells are the phthalocyanine (Pc) complexes of Co and Fe, and Co-TAA. FePc was found to be soluble in $\text{SOCl}_2/\text{LiAlCl}_4$ and, therefore, its use is limited to reserve cells. The cobalt and iron phthalocyanines have apparently been chosen previously for use as catalysts in Li/SOCl_2 cells because of their ability to catalyze the reduction of oxygen in fuel cells. Based on that criterion MnPc and VOPc should not function as active catalysts for SOCl_2 reduction, since they do not catalyze the reduction of oxygen well. Thus the use of MnPc and VOPc provided a test for the selection criteria of catalysts for use in the Li/SOCl_2 cell on the basis of their catalytic activity in fuel cells.

The phthalocyanines were dissolved in concentrated H_2SO_4 . Acetylene black carbon was mixed intimately with this solution and later washed with distilled water until the pH of the washings became neutral. The mixture was heat treated at 600°C under flowing Ar. Cathodes were fabricated in the usual way by mixing with Teflon binder followed by drying and sintering at 300°C in Ar atmosphere. The discharge results obtained at 10 mA/cm^2 at room temperature are summarized in Table 5.

Figure 12 depicts the discharge plot of a cell containing 5 percent VOPc. The load voltage is 3.35V. The capacity to 0.0V amounted to 1.98 Ah/g. The load voltage of the cell containing 10 percent VOPc was slightly lower but the cathode utilization was similar. VOPc shows a 45 percent improvement in capacity and a 10 percent improvement in cell voltage, both at 10 mA/cm².

The discharge behavior of a laboratory cell containing 5 percent MnPc-doped cathode is illustrated in Figure 13. The load voltage of this cell is about 50 mV lower than that of the VOPc containing cell; however, the capacity is higher. The cell containing a 10 percent load of MnPc performed worse than that containing 5 percent MnPc. It appears that the amount of catalyst is more critical with MnPc than with VOPc. The performance improvement attained with MnPc is a 60 percent increase in capacity and ~10 percent increase in cell voltage. The performance of MnPc at room temperature surpasses that of CoPc which we have evaluated to check the validity of our procedure. The discharge curve for the Li/SOCl₂ cell containing CoPc catalyzed cathodes is given in Figure 14. The performance we have achieved with CoPc is similar to what has been reported in the literature.⁴

Cells using cathodes which contained 5 percent loads of CoPc, VOPc, and MnPc were also discharged at -30°C, at a current density of 10 mA/cm². The results are summarized in Table 6. Discharge curves are presented in Figures 15 through 18. All the catalyzed cells showed higher mid-discharge voltages than the baseline cell. The VOPc catalyzed cell exhibited the best performance. The voltage regulation, compared with the baseline cell, was excellent, yielding practically all the capacity at a constant potential. This is extremely significant, since uncatalyzed cells usually exhibit a downward sloping potential profile at low temperatures, yielding a significant fraction of the capacity at potentials below 2.0V; Figure 18.

Cells containing CoPc and MnPc catalyzed cathodes also showed better voltage regulation at -30°C (Figures 16 and 17). However, their capacities were somewhat lower than that of the baseline cathode.

The preliminary results obtained so far with transition metal complex catalyzed cathodes indicate that MnPc is the preferred catalyst from the standpoint of performance at room temperature, while VOPc is the preferred material for applications involving both room and low temperatures. On the other hand, it is possible that a mixture of VOPc and MnPc might be the best catalyst composition for superior cell performance at both room and low temperatures.

We have also carried out discharges of Li/SOCl₂ cells containing cathodes doped with 5 w/o Co-TAA. This Co-TAA was synthesized by a different procedure¹² than the material previously reported.^{1,2} It showed a slightly different IR spectrum than the previous material (discussed later). Co-TAA was dissolved in dimethyl formamide (DMF) (1 ml DMF/1.5 mg Co-TAA) and mixed with Shawinigan acetylene black carbon. DMF was removed by heating the mixture at 70°C under vacuum. Cathodes were made by blending the dried carbon-Co-TAA mix with 10 w/o Teflon binder and spreading it onto Ni screens. After drying overnight at 100°C to remove water, the cathodes were sintered at 300°C for 20 minutes under flowing Ar.

The discharge performance of Co-TAA catalyzed laboratory Li/SOCl₂ cells at room temperature and at two different rates is illustrated in Figure 19. At 5 and 10 mA/cm² discharge rates, the cathode utilizations were 2.02 and 1.75 Ah/g,




FIGURE 15. DISCHARGE PLOT OF A CELL CONTAINING 5% VOPc-DOPED CATHODE




FIGURE 16. DISCHARGE PLOT OF A CELL CONTAINING 5% MnPc-DOPED CATHODE




FIGURE 17. DISCHARGE PLOT OF A CELL CONTAINING 5% CoPc-DOPED CATHODE




FIGURE 18. DISCHARGE PLOT OF AN UNCATALYZED CELL





FIGURE 19. AMBIENT TEMPERATURE DISCHARGE PERFORMANCE OF LABORATORY Li/SOCl₂ CELLS CONTAINING 5 w/o OF THE Co-TAA-DOPED CATHODES PREPARED BY THE TEMPLATE SYNTHESIS

respectively. The average load potential of these cells at 5 mA/cm² was 3.37V, while that at 10 mA/cm² was 3.2V.

MECHANISM OF ELECTROCATALYSIS IN Li/SOCl₂ CELLS

Our tentative model for electrocatalysis in Li/SOCl₂ cells is schematically illustrated below. This scheme suggests the formation of an adsorption complex between SOCl₂ and the catalyst, followed by reduction of the complex, and desorption of the reduction products. The actual mechanism might be more complex than the one illustrated. Considerable experimental data are required to fully elucidate the mechanism of electrocatalysis in Li/SOCl₂. It also remains to be established whether the same mechanism can explain catalysis by all catalysts that have so far been identified.



X-ray analysis of the catalyzed cathodes was performed before and after their use in Li/SOCl₂ cells. The results are presented in Tables 7 to 9.

The X-ray data for the various catalyst-doped cathodes given in Table 7 show that only with CoCO₃ precursors could any assignment of the catalyst species be made. The X-ray data seem to indicate that several cobalt carbides and Co₃O₄ are formed in the thermal treatment of the CoCO₃ impregnated carbon. The transition metal macrocyclic complex catalyzed cathodes only show the carbon lines. However, the X-ray data strongly suggest that these cathodes do not contain any oxides or carbides as the peaks for those species are absent. These analyses were performed with 10 percent doped electrodes. At such low levels of catalyst, poorly crystalline materials will escape detection. X-ray analysis on carbon doped with higher levels of catalyst will be performed in the near future.

The data in Tables 8 and 9 indicate that in the case of VOPc and MnPc catalysis, LiCl is a discharge product. Because these cells are flooded, most of the S would go into solution, thereby escaping detection by X-ray. The strongest S line is present in the X-ray patterns of the MnPc catalyzed cathode. Clearly, these data are insufficient to draw a picture of the mechanism of electrocatalysis. However, the absence of Li₂O suggest that no significantly different products from those formed in baseline cells are probably formed. Further analysis, including quantitative analysis of Cl⁻, S, and SO₂ will be performed in future studies.

TABLE 7. X-RAY DATA FOR THE UNDISCHARGED CATHODES
CONTAINING THE VARIOUS DOPANTS

Dopant Level (wt %)	Sintering Temperature (°C)	d, Å	I/I ₀	Assignment
20% CoCO ₃	500	7.34	100	Carbon
		4.85	50	Carbon
		2.45	45	Co ₂ C, Co ₃ C, Co ₃ O ₄
		2.12	68	Co ₂ C, Co ₃ C
		1.48	30	
20% Co(NO ₃) ₂	900	7.41	100	Carbon
		4.91	35	Co(NO ₃) ₂ , Carbon
10% VOPc	600	7.34	100	Carbon
		4.88	17	Carbon
		3.46	Trace	Carbon
10% MnPc	600	7.34	100	Carbon
		4.85	23	Carbon
		3.17	13	
5% CoPc	600	7.34	100	Carbon
		4.86	30	Carbon
10% Co ₄ (CO) ₁₂	200	7.34	100	Carbon
		3.59	60	
		1.95	30	

TABLE 8. X-RAY DATA FOR THE CATHODE OF A Li/SOCl_2 LABORATORY CELL CONTAINING 5 w/o VOPc AS CATHODE DOPANT AND DISCHARGED AT 10 mA/cm^2

$d, \text{\AA}$	I/I_0	Assignment
3.85	Trace	S
2.97	100	LiCl
2.58	90	LiCl
1.83	60	LiCl
1.56	30	LiCl
1.48	10	LiCl
1.29	Trace	LiCl
1.18	10	LiCl
1.15	10	LiCl
1.05	10	LiCl
0.99	10	LiCl
0.91	Trace	LiCl
0.87	Trace	LiCl
0.86	Trace	LiCl
0.82	Trace	LiCl

TABLE 9. X-RAY DATA FOR THE CATHODE OF A Li/SOCl_2 LABORATORY CELL CONTAINING 5 w/o MnPc AS CATHODE DOPANT AND DISCHARGED AT 10 mA/cm^2

$\frac{d, \text{\AA}}{d, \text{\AA}}$	I/I_0	Assignment
4.81	Trace	C
3.85	20	S
3.47	Trace	
3.20	Trace	LiAlCl_4
3.08	Trace	
2.97	100	LiCl
2.84	Trace	LiAlCl_4
2.73	90	
2.57	90	LiCl
2.42	Trace	
2.29	10	
1.93	10	
1.87	Trace	LiAlCl_4
1.82	50	LiCl
1.73	Trace	LiAlCl_4
1.57	20	
1.55	30	LiCl
1.46	20	LiCl
1.36	Trace	
1.29	Trace	LiCl
1.22	Trace	
1.18	10	LiCl
1.15	20	LiCl
1.05	20	LiCl
1.03	Trace	
0.99	20	LiCl
0.87	20	LiCl
0.86	20	LiCl
0.81	10	LiCl

The IR spectrum of Co-TAA prepared by two different methods is illustrated in Figures 20 and 21. Comparison of these spectra reveal that Co-TAA as prepared by Reference 2, and previously discussed in Reference 1, is possibly somewhat different from that prepared by the template synthesis described in Reference 12. Studies to evaluate these differences are in progress.




FIGURE 20. IR SPECTRUM OF Co-TAA SYNTHESIZED BY THE CONVENTIONAL METHOD (1,2)




FIGURE 21. IR SPECTRUM OF Co-TAA PREPARED BY THE TEMPLATE SYNTHESIS (12)

CHAPTER 4

CONCLUSIONS

Doping acetylene black carbon with cobalt species generated by the thermal decomposition of CoCO_3 , $\text{Co}_2(\text{CO})_8$, and $\text{Co}_4(\text{CO})_{12}$ did not result in cathodes suitable for catalyzing the discharge reaction of the Li/SOCl_2 cell. X-ray analysis revealed that CoCO_3 impregnated carbon generates cobalt carbides and Co_3O_4 upon thermal treatment at 500°C . The dopant species derived from $\text{Co}_2(\text{CO})_8$ and $\text{Co}_4(\text{CO})_{12}$ could not be identified by X-ray.

Mixing acetylene black with $\text{Co}(\text{NO}_3)_2$ followed by thermal treatment resulted in increased capacity for the electrode. The cell voltage remained the same as in baseline Li/SOCl_2 cells. Further studies, especially with regard to the amount of $\text{Co}(\text{NO}_3)_2$ and optimum temperature for thermal treatment, are needed.

Acetylene black carbon impregnated with transition metal phthalocyanines, followed by sintering at 600°C , resulted in highly enhanced capacity and higher cell voltage for the high rate discharge (viz., $10 \text{ mA}/\text{cm}^2$) of Li/SOCl_2 cells. Two new catalysts, VOPc and MnPc, have been discovered. These catalysts appear to be superior to many of the catalysts presently available. MnPc-containing cathodes showed a 60 percent increase in capacity and a 10 percent increase in cell voltage at $10 \text{ mA}/\text{cm}^2$ at room temperature. VOPc-containing cathodes increased the cell capacity by 45 percent and cell voltage by 10 percent at $10 \text{ mA}/\text{cm}^2$ at room temperature. VOPc also improved cell performance significantly at -30°C .

Currently available data indicate that transition metal macrocyclic complexes have special features that allow catalytic activity for the discharge of Li/SOCl_2 cells. The fact that VOPc and MnPc are highly active for SOCl_2 reduction, while inactive in fuel cells for O_2 reduction, suggests that the criteria for selection of catalysts for the reduction of SOCl_2 are different from those in fuel cells.

MnPc, VOPc, and CoPc were incorporated into the carbon by heating at 600°C . At these temperatures, these complexes are known to decompose. Questions remain about the nature of the active catalyst species when phthalocyanines are used. X-ray analysis did not provide the necessary answers because of the low concentrations of the catalyst species. Further work is planned.

Limited analyses of discharged cathodes seem to suggest that the discharge products are most probably LiCl , SO_2 , and S , as in uncatalyzed cells. Quantitative analysis remains to be performed.

The new catalysts VOPc and MnPc appear to be of considerable potential for practical use. Therefore, further studies exploring the full extent of the usefulness of these new catalysts in practical batteries should be performed.

Additional studies are required to explain any differences in the catalysis process arising from samples reported to be Co-TAA but, as indicated by IR data, possibly differ in structure.

REFERENCES

1. Abraham, K. M.; Pitts, L.; and Kilroy, W. P., J. Electrochem. Soc., Vol. 132, 1985, p. 2301.
2. Walsh, F. and Yaniv, M., ERADCOM Technical Report, DELET-TR-83-0386-F, May 1984 (also refer to paper to be given by D. Barinelli and F. Walsh at 33rd Power Sources Symposium, Cherry Hill, NJ, Jun 1988).
3. Schlaikjer, C. R., Chapter 13 in Lithium Batteries, J. P. Gabano, Ed., Academic Press, 1983.
4. Doddapaneni, N., Proceedings of the 31st Power Sources Symposium, Cherry Hill, NJ, The Electrochemical Society, p. 411, 1984.
5. Klinedinst, K. A., J. Electrochem. Soc., Vol. 128, 1981, p. 2504.
6. Behl, W. K., J. Electrochem. Soc., Vol. 128, 1981, p. 939.
7. Klinedinst, K. A. and Gary, R. A., U.S. Patent 4,452,872.
8. Abraham, K. M. and Alamgir, M., J. Electrochem. Soc., Vol. 124, 1987, p. 258.
9. Scherson, D. A. et al., Electrochim. Acta, Vol. 28, 1983, p. 1205.
10. Wiesener, K., Electrochim. Acta, Vol. 31, 1986, p. 1073.
11. Jahnke, H.; Schonborn, M.; and Zimmermann, G., Topics in Current Chemistry, Vol. 61, 1976, p. 133.
12. Chave, P. and Honeybourne, C. L., Chemical Communications, 1969, p. 279.
13. Krustinsons, J., Z. Elektrochem., Vol. 39, 1933, p. 936.
14. The Handbook of Chemistry and Physics, The Chemical Rubber Company Press, 63rd Edition, 1983.

DISTRIBUTION

	<u>Copies</u>		<u>Copies</u>
Defense Technical Information Center		Naval Sea Systems Command	
Cameron Station		Attn: Code 56Z33 (E. Anderson)	1
Alexandria, VA 22304-6145	12	SEA-06H3 (H. Holter)	1
		Washington, DC 20362	
Defense Nuclear Agency		Strategic Systems Project Office	
Attn: Library	1	Attn: Code NSP 2721 (K. N. Boley)	1
Washington, DC 20301		Code NSP 2722 (M. Meserole)	1
		Washington, DC 20360	
Institute for Defense Analyses		Naval Air Development Center	
R&E Support Division		Attn: Code 6012 (J. Segrest)	1
400 Army-Navy Drive	1	Code 30412 (R. Schwartz)	1
Arlington, VA 22202		Code 3042 (L. B. Hanson)	1
Library of Congress		Warminster, PA 18974	
Attn: Gift and Exchange Div.	4	Naval Intelligence Support Center	
Washington, DC 20540		Attn: Code 362 (Dr. H. Ruskie)	1
Office of Naval Research		Washington, DC 20390	
Attn: Code ONR 472 (R. Nowak)	1	Naval Ocean Systems Center	
800 North Quincy Street		Attn: Code 6343 (Dr. S. Szpak)	1
Arlington, VA 22217		Code 6343 (L. Johnson)	1
Naval Research Laboratory		San Diego, CA 92152	
Attn: Code NRL 6130 (A. Simon)	1	U.S. Development and Readiness Command	
Chemistry Division		Attn: Code DRCDE-L	
4555 Overlook Avenue, SW		(J. W. Crellin)	1
Washington, DC 20375		5001 Eisenhower Avenue	
Naval Air Systems Command		Alexandria, VA 22333	
Attn: Code NAVAIR 301C		Army Material and Mechanical Research Center	
(Dr. H. Rosenwasser)	1	Attn: J. J. Demarco	1
Washington, DC 20361		Watertown, MA 02172	
Space and Naval Warfare Systems Command		USA Mobility Equipment R&D Command	
Attn: Code PME 124-31		Attn: Code DRXFB (J. Sullivan)	1
(A. H. Sobel)	1	Code DRME-EC	1
Code 01K (T. Sliwa)	1	Electrochemical Division	
M. Costa	1	Fort Belvoir, VA 22060	
Washington, DC 20360			

DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
Edgewood Arsenal		Naval Weapons Support Center	
Attn: Library	1	Attn: Code 305 (M. Robertson)	1
Aberdeen Proving Ground		D. Mains	1
Aberdeen, MD 21010		Code 3054 (S. Shuler)	1
		W. Johnson	1
U.S. Army		R. Haag	1
Picatinny Arsenal		Electrochemical Power Sources Div.	
Attn: Code SAROA-FR-E-L-C		Crane, IN 47522	
(Dr. B. Werbel)	1		
Code SARPA-ND-D-B		Naval Coastal Systems Center	
(A. E. Magistro)	1	Attn: Library	1
Dover, NJ 07801		Panama City, FL 32407	
Harry Diamond Laboratories		Naval Underwater Systems Center	
Attn: Code DELHD-DE-OP		Attn: Code SB332 (J. Model)	1
(J. T. Nelson)	1	P. Hallal	1
M. Templeman	1	Newport, RI 02840	
Department of Army Material			
Chief, Power Supply Branch		David Taylor Research Center	
2800 Powder Mill Road		Annapolis Laboratory	
Adelphi, MD 20783		Annapolis, MD 21402	1
HQ, Department of Transportation		Air Force Wright Aeronautical Labs	
Attn: Code GEOE-3/61 (R. Potter)	1	Aero Propulsion Lab., POOC	
U.S. Coast Guard		Attn: Code AFAPL/POE-1	
Ocean Engineering Division		(W. S. Bishop)	1
Washington, DC 20590		Code AFWAL-POOS-2	
		(R. Marsh)	1
NASA Headquarters		Wright-Patterson AFB, OH 45433	
Attn: Dr. J. H. Ambrus	1		
Washington, DC 20546		Air Force Rocket Propulsion Lab	
		Attn: Code MKPA	
NASA Lewis Research Center		(Lt. D. Ferguson)	1
Attn: Code MS309-1		Edwards Air Force Base, CA 93523	
(J. S. Fordyce)	1		
M. Reid	1	HQ, Air Force Special	
2100 Brookpark Road		Communications Center	
Cleveland, OH 44135		Attn: Library	1
		USAFSS	
Naval Weapons Center		San Antonio, TX 78243	
Attn: Code 38 (Dr. E. Royce)	1		
Code 3852 (Dr. A. Fletcher)	1	Office of Chief of R&D	
Dr. J. Smith	1	Department of the Army	
D. Rosenlof	1	Attn: Dr. S. J. Magram	1
W. Haight	1	Energy Conversion Branch	
China Lake, CA 93555		Room 410, Highland Building	
		Washington, DC 20315	

DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
U.S. Army Research Office		Frank J. Seiler Research Lab, AFSC	
Attn: B. F. Spielvogel	1	USAF Academy, CO 80840	1
G. Neece	1		
P. O. Box 12211		Department of National Defense	
Research Triangle Park, NC 27709		Attn: Library	1
		W. Adams	1
NASA Scientific and Technical		G. Donaldson	1
Information Facility		J. Lackner	1
Attn: Library	1	Defense Rsch Establishment Ottawa	
Code 711.2 (T. Yi)	1	Ottawa, Ontario K1A 0Z4 Canada	
P. O. Box 33			
College Park, MD 20740		NASA Johnson Space Center	
		Attn: EPS (Bob Bragg)	1
National Bureau of Standards		Houston, TX 77058	
Metallurgy Division			
Inorganic Materials Division		Office of Naval Technology	
Washington, DC 20234	1	Attn: MAT072 (A. J. Faulstich)	1
		(G. Spaulding)	1
U.S. Army Electronics Command		800 North Quincy Street	
Attn: Code DRSEL-TL-P		Arlington, VA 22217	
(A. J. Legath)	1		
Code DRSEL-TL-PD		Central Intelligence Agency	
(E. Brooks)	1	Attn: OTS (C. Sculla)	1
G. DiMasi	1	T. Mahy	1
Dr. W. K. Behl	1	Washington, DC 20505	
Code DELET-PR			
(Dr. Sol Gilman)	1	ARDC	
C. Berger	1	Attn: D. Yedwab	1
M. Salomon	1	LOWSL-LCN	
E. Reiss	1	Building 61 South	
J. Perry	1	Dover, NJ 07801	
R. Mohlenhoff	1		
M. Brundage	1	HQ, U.S. Marine Corps	
D. Barker	1	Attn: LMA-3 (LTCOL W. Lowe)	1
Fort Monmouth, NJ 07703		Washington, DC 20380	
Scientific Advisor		Missile Systems Safety	
Attn: Code AX	1	Attn: ESMC/SEM (Kenn Hill)	1
Commandant of the Marines		Patrick AFB, FL 32925	
Washington, DC 20380			
Air Force of Scientific Research			
Attn: Dir. of Chemical Science	1		
1400 Wilson Boulevard			
Arlington, VA 22209			

DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
California Institute of Technology		U.S. Naval Academy	
Attn: Library	1	Attn: Dr. G. T. Cheek	1
R. Somoano	1	Chemistry Department	
H. Frank	1	Annapolis, MD 21402	
S. Yen	1		
G. Halpert	1	University of Wisconsin-Milwaukee	
S. Dawson	1	Attn: Dr. D. Bennett	1
D. Shen	1	Chemistry Department	
A. Attia	1	3210 North Cramer Street	
C. Jaeger	1	Milwaukee, WI 53201	
S. Surampuda	1		
Jet Propulsion Laboratory		State University of New York	
4800 Oak Grove Drive		Attn: Dr. R. A. Osteryoung	1
Pasadena, CA 91109		Department of Chemistry	
		Buffalo, NY 14214	
Johns Hopkins Applied Physics Lab		University of Rome	
Attn: Library	1	Attn: Dr. B. Scrosati	1
M. Uy	1	Istituto di Chimica Fisica	
Johns Hopkins Road		P. le A. Moro 5, 00185 Rome, Italy	
Laurel, MD 20707			
University of Tennessee		Brookhaven National Laboratory	
Attn: G. Mamantov	1	Attn: J. Sutherland	1
Department of Chemistry		Building 1815	
Knoxville, TN 37916		Upton, NY 11973	
Applied Research Laboratory		Argonne National Laboratory	
Attn: Library	1	Attn: Dr. E. C. Gay	1
Penn State University		Dr. D. Vissars	1
University Park, PA 16802		Dr. J. Rajan	1
		9700 South Cass Avenue	
University of Illinois at Chicago		Argonne, IL 60439	
Attn: Dr. R. Burns	1	Lawrence Berkeley Laboratory	
Department of Chemistry		Attn: F. McLamore	1
Chicago, IL 60680		University of California	
Tel-Aviv University		Berkeley, CA 94720	
Attn: E. Peled	1		
Department of Chemistry		Oak Ridge National Laboratory	
Tel Aviv, Israel 69978		Attn: K. Braunstein	1
		Oak Ridge, TN 37830	
University of California			
Attn: Dr. R. A. Huggins	1		
Dept. Material Science & Engr.			
Stanford, CA 94305			

DISTRIBUTION (Cont.)

<u>Copies</u>	<u>Copies</u>
Sandia Laboratories	Yardney Electric Corporation
Attn: Mail Services Sect. 3154-3	Attn: Library 1
(Sam Levy) 1	82 Mechanic Street
J. T. Cutchen 1	Pawcatuck, CT 02891
N. Godshall 1	Honeywell Corporate Technology Ctr
N. Magnani 1	Attn: H. V. Venkatesetty 1
H. Saxtor 1	10701 Lyndale Avenue, South
P. O. Box 5800	Bloomington, MN 55420
Albuquerque, NM 87715	
Ministere de la defense nationale	Honeywell, Inc.
Attn: Dr. W. Adams 1	Material & Process Engr.
Dr. G. Donaldson 1	Attn: MN11-1812 (K. Y. Kim) 1
Centre de recherches pour la defense	600 2nd Street, NE
Ottawa, Ontario K1A 0Z4 Canada	Hopkins, MN 55343
Nippon Telegraph and Telephone Corporation	The Aerospace Corporation
Attn: Dr. J. Yamaki 1	Attn: H. Bittner 1
NTT Applied Electronics Laboratories	A. Heller 1
Tokai-Mura, Naka-Gun	S. Donley 1
Ibaraki-Ken, 319-11 Japan	W. Stafford 1
	P. O. Box 92957
Chemtech Systems, Inc.	Los Angeles, CA 90009
Attn: Dr. M. L. Gopikanth	Honeywell Power Sources Corporation
P. O. Box 1067	Attn: Dr. D. L. Chua 1
Burlington, MA 01803	N. Doddapaneni 1
SAFT	104 Rock Road
Attn: Dr. J. P. Gabano 1	Horsham, PA 19044
Dept Generateurs de Technologies	Battelle Memorial Institute
Advances	Defense Metals & Ceramics
Rue Georges Leclance	Information Center
BP 357-86009 Poitiers, France	505 King Avenue
	Columbus, OH 43201 1
Union Carbide Corporation	Bell Laboratories
Battery Products Division	Attn: Dr. J. J. Auburn 1
Attn: G. E. Blomgren 1	600 Mountain Avenue
P. O. Box 45035	Murray Hill, NJ 07974
Westlake, OH 44145	
Wilson Greatbatch Ltd.	Callery Chemical Company
Attn: Library 1	Attn: Library 1
R. M. Carey 1	Callery, PA 16024
C. Holmes 1	Rockwell International
Dr. W. Clark 1	Attn: Dr. S. J. Yosim 1
1000 Wehrle Drive	Atomics International Division
Clarence, NY 14030	8900 DeSoto Avenue
	Canoga Park, CA 91304

DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
EDO Corporation		Catalyst Research Corporation	
Attn: E. P. DiGiannantonio	1	Attn: G. Bowser	1
Government Products Division		J. Joelson	1
2001 Jefferson Davis Highway		A. Schneider	1
Arlington, VA 22202		1421 Clarkview Road	
		Baltimore, MD 21209	
Globe Union, Inc.			
Attn: Dr. R. A. Rizzo	1	ESB Research Center	
5757 North Green Bay Avenue		Attn: Library	1
Milwaukee, WI 53201		19 West College Avenue	
		Yardley, PA 19067	
RAI Research Corporation			
Attn: Dr. C. Perini	1	EIC Laboratories, Inc.	
225 Marcus Boulevard		Attn: G. L. Holleck	1
Hauppauge, NY 11787		K. M. Abraham	10
		M. Alamgir	10
Battery Engineering, Inc.		111 Downey Street	
Attn: Dr. N. Marincic	1	Norwood, MA 02062	
P. Kane	1		
C. Schlaikjer	1	Eagle-Picher Industries, Inc.	
1636 Hyde Park Avenue		Attn: R. L. Higgins	1
Hyde Park, MA 02136		J. Dines	1
		L. R. Erisman	1
RAY-O-VAC		Electronics Division	
Attn: N. Fleischer	1	P. O. Box 47	
630 Forward Drive		Joplin, MO 64802	
Madison, WI 53711			
		Foote Mineral Company	
Litton Data Systems Division		Attn: H. R. Grady	1
Attn: MS 64-61 (Frank Halula)	1	Exton, PA 19341	
800 Woodley Avenue			
Van Nuys, CA 91409		Gould, Inc.	
		Attn: S. S. Nielsen	1
TRW Systems		40 Gould Center	
Attn: I. J. Groce	1	Rolling Meadows, IL 60008	
G. L. Juvinat	1		
E. Moon	1	GTE Laboratory	
One Space Park		Attn: R. McDonald	1
Redondo Beach, CA 90278		K. Kliendienst	1
		40 Sylvan Road	
Altus Corporation		Waltham, MA 02254	
Attn: Dr. A. E. Zolla	1		
Library	1	Strategic Systems Division	
1610 Crane Court		GTE Government Systems Corp.	
San Jose, CA 95112		Attn: F. Dampier	1
		520 Winter Street	
Hyde Park Estates		Waltham, MA 02254	
Attn: Dr. P. Bro	1		
Sante Fe, NM 87501			

DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
Hughes Aircraft Company		Cordis Corporation	
Attn: Dr. L. H. Fentnor	1	Attn: W. K. Jones	1
Aerospace Groups		P. O. Box 525700	
Missile Systems Group		Miami, FL 33152	
Tucson Engr Laboratory			
Tucson, AZ 85734		Tadiran	
		Attn: M. Babai	1
Lockheed Missiles & Space Co., Inc.		P. O. Box 75	
Attn: Library	1	Rehovot, Israel	
Lockheed Palo Alto Rsch Lab			
3251 Hanover Street		Power Conversion, Inc.	
Palo Alto, CA 04304		Attn: Dr. T. Reddy	1
		495 Boulevard	
Duracell International, Inc.		Elmwood Park, NJ 07407	
Attn: B. McDonald	1		
Battery Division		Covalent Associates, Inc.	
South Broadway		Attn: Dr. V. Koch	1
Tarrytown, NY 10591		52 Dragon Court	
		Woburn, MA 01801	
Duracell International, Inc.			
Attn: W. Bowden	1	MoLi Energy Limited	
A. N. Dey	1	Attn: Dr. J. A. Stiles	1
F. Parsons	1	4010 Myrtle Street	
Library	1	Burnaby, BC V5C 4G2 Canada	
Duracell Research Center			
37 A Street		ECO	
Needham, MA 02194		Energy Conversion	
		Attn: Dr. F. M. Walsh	1
Boeing Aerospace Company		225 Needham Street	
Attn: S. Gross	1	Newton, MA 02164	
C. Johnson	1		
P. O. Box 3999		Ansum Enterprises, Inc.	
Seattle, WA 98124		Attn: Dr. S. P. Wolsky	1
		950 DeSoto Road	
Electrochimica Corporation		Boca Raton, FL 33432	
Attn: M. Eisenberg	1		
2485 Charleston Road		Advanced Battery Group	
Mt View, CA 94040		Attn: Dr. R. M. Murphy	1
		269 Westwood Road	
Eltron Research		Lancaster, NY 14086	
Attn: T. Sammells	1		
710 East Ogden Avenue		Medtronics, Inc.	
Naperville, IL 60540		Attn: Dr. D. Untereker	1
		6700 Shingle Creek Parkway	
Saft America, Inc.		Brooklyn Center, MN 55430	
Attn: Dr. R. J. Staniewicz	1		
Dr. K. Press	1		
Dr. G. Allvey	1		
107 Beaver Court			
Cockeysville, MD 21030			

DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
ELTECH Systems Corporation		Amoco Corporation	
Attn: D. E. Harney	1	Attn: Dr. J. N. Gleeson	1
Research & Development Center		Amoco Research Center	
625 East Street		P. O. Box 400	
Fairport Harbor, OH 44077		Naperville, IL 60566	
 Harkness Consultants Inc.		 Power Information Center	
Attn: Dr. A. C. Harkness	1	CSR, Inc.	
Suite 1601		1400 Eye Street, N.W.	
150 - 24th Street		Suite 600	
West Vancouver, BC V7V 4G8 Canada		Washington, DC 20005	1
 Dr. Boone B. Owens	1	 Internal Distribution:	
P. O. Box 8205		E231	2
St. Paul, MN 55108		E232	15
		E35	1
 Ultra Technologies - KODAK		R33 (W. P. Kilroy)	50
Attn: P. F. Dickinson	1		
P. O. Box 267			
Rt. 88 South			
Newark, NY 14513			

END

DATE

FILMED

DTIC

JULY 88